

SLX-III NIJ LEVEL IIIA SOFT ARMOR



Constructed of Twaron / Dyneema ballistic material

NIJ 0101.06 Certified Level IIIA

Weight: 0.86 psf.

Thickness: 0.21"

CERTIFICATION TEST RESULTS

V50 - 357sig 125gr FMJ (new) 1862 ft/s (567 m/s)

V50 - 357sig 125gr FMJ (conditioned) 1808 ft/s (551 m/s)

P-BFS Avg. - 357sig 125gr FMJ 27 mm

V50 - 44mag 240gr SJHP (new) 1749 ft/s (533 m/s)

V50 - 44mag 240gr SJHP (conditioned) 1744 ft/s (531 m/s)

P-BFS Avg. - 44mag 240gr SJHP 35 mm

SPECIAL THREAT TESTING

V50 - 2gr RCC 3019 fps (920 m/s)

V50 - 4gr RCC 2658 fps (810 m/s)

V50 - 16gr RCC 2265 fps (690 m/s)

V50 - 17gr FSP (.22cal) 2012 fps (613 m/s)

V50 - 64gr RCC 1801 fps (549 m/s)

V50 - 9mm 127gr STX 1748 fps (533 m/s)

P-BFS Avg. - 9mm 127gr SXT 28 mm

V50 - 40cal 165gr GDHP NA*

P-BFS Avg. - 40cal 165gr GDHP 27 mm

V50 - 5.7x28mm 27gr SS195 HP 2549 fps (777 m/s)

P-BFS Avg. - 5.7x28mm 27gr SS195 HP 14 mm

V50 - 5.7x28mm 40gr SS197 SR 2402 fps (732 m/s)

P-BFS Avg. - 5.7x28mm 40gr SS197 SR 20 mm

V50 - 7.62x25mm TOK SJLC 1794 fps (547 m/s)

P-BFS Avg. - 7.62x25mm TOK SJLC 23 mm

